



**Graver Technologies**

**Quality Department**

**GRAVEX<sup>®</sup>  
GR 2-0 NA  
SODIUM FORM**

<b>SPEC NO</b>	GTS-20-Na
<b>REV NO</b>	1
<b>DATE</b>	October 18, 1999
<b>QA APPROVAL</b>	<i>Keith Platoff</i>

**PROPERTIES**

Resin Type	Strongly Acidic Cation Exchange Resin
Functionality	Sulfonic Acid
Matrix	Styrene-Divinylbenzene
Total Exchange Capacity	2.2 meq/mL (min)
Percent of Sites	99% Sodium (min)
Water Retention Capacity	40-46% (max)
Particle Size	5% plus 16 mesh (1.2 mm) (max)
	5% minus 40 mesh (0.4 mm) (max)
	0.5% minus 50 mesh (0.3 mm) (max)
Metals (mg/dry kg)	50 Iron (max)
	10 Copper (max)
Shipping Weight	53 lbs/cu. ft. (850 g/L)

**SPECIFICATIONS**