



Graver Technologies

Quality Department

**GRAVEX®
GR 2-0
HYDROGEN FORM**

SPEC NO	GTS-20-S
REV NO	4
DATE	April 25, 2001
QA APPROVAL	<i>Keith Platoff</i>

PROPERTIES

Resin Type

Functionality

Matrix

Total Exchange Capacity

Percent of Sites

Particle Size

Metals (mg/dry kg)

Shipping Weight

SPECIFICATIONS

Strongly Acidic Cation Exchange Resin

Sulfonic Acid

Styrene-Divinylbenzene

2 meq/mL (min)

99% Hydrogen (min)

5 % plus 16 mesh (max)

5% minus 40 mesh (max)

0.5% minus 50 mesh (max)

50 Sodium (max)

50 Iron (max)

10 Copper (max)

50 lbs/ft³ (801 g/L)